

# PRODUCT DATA SHEET

## Earthing components

### Substation earthing

**Code: 1026403-70**

**Description: Mould for exothermic welding 120mm<sup>2</sup> Cu / 70mm<sup>2</sup> Cu in "T", type THH-AA-120/70, code: 1026403**

#### Application

Connection of copper conductors through exothermic welding. The welding takes place in a graphite mould-crucible, into which has been introduced welding powder and the pieces to be welded. The powder is ignited by the starting powder using a flint igniter. Molted metal from the exothermic reaction flows over the pieces, causing them to be melted and fused into a solid homogeneous mass.



#### Classification as per IEC EN 62561

- Heavy duty (H - 100 kA)
- General use
- Intended to withstand a static mechanical load
- Permanent connection

#### Installation data - Needed equipment

Conductor's dimensions	120 mm <sup>2</sup> stranded / 70 mm <sup>2</sup> stranded.
Conductor's material	Copper / Copper.
Connection arrangement	"T" (B4).
Installation	Outdoor, buried in ground, embedded in concrete.

Needed  
equipment

Exothermic powder 90 gr (code 1820090-70), handle clamp (code 1930160-70), mould cleaner (code 1900007-70), flint igniter (code 1910032-70), soft brush for cleaning the inner part of the mould (code 1980313-70), wire brush used for cleaning the conductors (code 1950000-70), mould seal (code 1920315-70).

### Testing as per IEC EN 62561

The above exothermic powder has successfully passed the testing requirements of standard IEC EN 62561-1 "Lightning protection system components (LPSC) – Part 1 : Requirements for connection components".

Test reports No **30934-I & 30944-I** by accredited laboratory as per ISO 17025.

### ELEMKO management systems

- ISO 9001
- ISO 14001
- ISO 45001

### Country of Origin

Greece

### Unit: piece / Package: 1 piece

We reserve the right to introduce changes in the component due to technical evolution.