

PRODUCT DATA SHEET LIGHTNING PROTECTION AND EARTHING SYSTEM COMPONENTS	
Type: PHH-BB-403/403 ed.02/2021	
	ermic welding 40x3 mm Cu / 40x3 mm Cu in parallel connection
takes place in a grap powder and the piece using a flint igniter. Mo causing them to be me Classification as p • Heavy duty (H – 10 • General use	00 kA) nd a static mechanical load tion
Code	Description
15 21 301	Graphite mould of average last of 70-100 connections under normal conditions of use.
18 20 150	Exothermic powder
19 30 160	Handle clamp, allowing to open and close the mould safely
19 00 002	Mould cleaner, to remove the slag and to check tap hole clearance after making every weld
19 10 032	Flint igniter
19 80 313	Soft brush for safely cleaning the inner part of the mould after every weld
19 50 000	Wire brush used for cleaning the conductors before making the weld
19 20 315	Mould seal to prevent leakage of the molten weldmetal.
Installation data	
Conductor's dimensions	40x3 mm tape / 40x3 mm tape
Conductor's material Connection	Copper / Copper
arrangement	Parallel (B2)
Installation	Above ground, buried in ground, embedded in concrete
Note	For the welding procedure please refer to general instructions O.E.2.1-15, accompanying the mould. Especially for this mould, insert end of tap bus bar until centre of tap hole. Tap bus bar must be at least 70 mm parallel to the run bus bar.
Testing as per IEC	EN 62561
Testing as per IEC EN 62561 The above exothermic powder has successfully passed the testing requirements of standard IEC EN 62561-1 "Lightning protection system components (LPSC) – Part 1 : Requirements for connection components". Test report No 30820 by accredited laboratory as per ISO 17025	
Manufacturing Quality Control	
Manufacturing quality control according standard ISO 9001	
Country of Origin	
Greece	
	We reserve the right to introduce changes in the component due to technical evolutio